

Tender specifications | BIOARCH collection

Supply of Panaria Ceramica porcelain stoneware tiles for walls and floors.

Product characteristics

Panaria Ceramica coloured-body porcelain stoneware tiles, unglazed, composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C.

The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

Compliance with EN 14411-G / ISO 13006-G

The BIOARCH collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Panaria Ceramica in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation CE 1221/09 - eco-management and audit community system).

The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%, as certified by a qualified external body (LEED V4 Regulations - MR Credit).

The product contains no VOC (volatile organic compounds) and got the GREENGUARD GOLD certification.

The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the BIOARCH collection based on its Life Cycle Assessment (LCA).

For all the items in the collection, the calculation of the carbon footprint (PCF) over the entire life cycle is available, expressed as CO₂ equivalent per unit of product, certified according to ISO 14067.

The collection complies with the technical specifications and contractual conditions applicable to porcelain stoneware outlined in the Ministerial Decree of 23 June 2022 "Minimum environmental criteria for the contracting of the design and execution of works for building projects".

Commercial description of the product	
Company	PANARIA CERAMICA (Panariagroup Industrie Ceramiche S.p.A.)
Collection	BIOARCH
Colours	BARGE GIALLA, BARGE GRIGIA
Sizes	20x20 cm STRUTTURATO
	20x30,5 cm STRUTTURATO
	20x41 cm STRUTTURATO
Surfaces	STRUTTURATO
Edges	NOT RECTIFIED
Thickness	9 mm

Tender specifications | BIOARCH collection

Technical features

Product type: coloured-body porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features		Test method	Required values ISO 13006-G / EN 14411-G Bla-UGL Group	Average values BIOARCH
Water absorption	ISO 10545-3	≤ 0,5%	0,05%	
Breaking strength (S)	ISO 10545-4	≥ 1300 N	2200 N	
Modulus of rupture	ISO 10545-4	≥ 35 N/mm ²	50 N/mm ²	
Deep abrasion resistance	ISO 10545-6	≤ 175 mm ³	145 mm ³	
Linear thermal expansion	ISO 10545-8	No provision	α ≤ 7 · 10 ⁻⁶ °C ⁻¹	
Stain resistance	ISO 10545-14	Class 3 min.	5 RESISTANT	
Chemical resistance (*)	ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT	
Frost resistance	ISO 10545-12	No alteration	RESISTANT	
Dimensions	Length and width	ISO 10545-2	RECT ± 0,3%, max ± 1 mm	COMPLIANT
			± 0,6%, max ± 2 mm	
	Straightness of sides	ISO 10545-2	RECT ± 0,3%, max ± 0,8 mm	COMPLIANT
			± 0,5%, max ± 1,5 mm	
	Rectangularity	ISO 10545-2	RECT ± 0,3%, max ± 1,5 mm	COMPLIANT
			± 0,5%, max ± 2 mm	
Slip resistance	Warpage	ISO 10545-2	RECT ± 0,4%, max ± 1,8 mm	COMPLIANT
			± 0,5%, max ± 2 mm	
		ISO 10545-2	± 5% ± 0,5 mm	COMPLIANT
		DIN EN 16165 - Annex B	-	R11 (STRUTTURATO)
		DIN EN 16165 - Annex A	-	C (STRUTTURATO)
Shade variation	BCR-TORTUS	BCR-TORTUS	-	μ > 0,40 (STRUTTURATO)
		ANSI A326.3	-	EW (STRUTTURATO)
		BS EN 16165 - Annex C	-	PTV 36+Wet (SI.96 - SI.55): STRUTTURATO
		ANSI A137.1	As indicated by manufacturer	V4 (STRUTTURATO)
		EN 13823	CPR (UE) 305/2011, 2000/147/CE, UNI EN 13501-1	Class A1 (wall)
Fire reaction		EN 9239-1		Class A1 _f (floor)
Thermal conductivity	EN 12524	-	λ = 1,3 W/m °K	
Recommended minimum joint (**)	Outdoor	-	-	10 mm

(*) Excluding hydrofluoric acid and its derivatives.

(**) The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.

