

Tender specifications | PERPETUAL collection

Supply of Panaria Ceramica porcelain stoneware tiles for walls and floors.

Product characteristics

Panaria Ceramica coloured-body porcelain stoneware tiles, unglazed, composed of a very fine mixture of quality clay with the addition of feldspar, quartz and kaolin, manufactured by dry pressing of atomized powders and subsequently sintered by industrial firing at temperatures above 1200°C.

The complete vitrification of the tiles allows for a compact, non-absorbent, frost-proof product, resistant to bending, impacts, staining, chemical attack and thermal shock.

Compliance with EN 14411-G / ISO 13006-G

The PERPETUAL collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Panaria Ceramica in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognized standard) and EMAS (Regulation CE 1221/09 - eco-management and audit community system).

The collection helps to meet the criteria for obtaining LEED credits. The content of "pre-consumer" recycled material is 40%, as certified by a qualified external body (LEED V4 Regulations - MR Credit).

The product contains no VOC (volatile organic compounds) and got the GREENGUARD GOLD certification.

The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the PERPETUAL collection based on its Life Cycle Assessment (LCA).

For all the items in the collection, the calculation of the carbon footprint (PCF) over the entire life cycle is available, expressed as CO₂ equivalent per unit of product, certified according to ISO 14067.

The collection complies with the technical specifications and contractual conditions applicable to porcelain stoneware outlined in the Ministerial Decree of 23 June 2022 "Minimum environmental criteria for the contracting of the design and execution of works for building projects".

Antibacterial properties

Thanks to Protect antibacterial technology, the tiles from the PERPETUAL collection have continuous, effective and durable protection against the proliferation of bacteria, tested and certified in accordance with ISO 22196 and ASTM E3031.

| Commercial description of the product | | | | | |
|---------------------------------------|---|---------------------|-------------------------|--------------------|----------------------------|
| Company | PANARIA CERAMICA (Panariagroup Industrie Ceramiche S.p.A.) | | | | |
| Collection | PERPETUAL | | | | |
| Colours | VENATO GOLD, BRECCIA WARM, ONICE CLEAR, OROBICO BLEND, BELVEDERE DARK, TRAVERTINO IVORY, TRAVERTINO CREAM | | | | |
| Sizes | 60x60 cm Rect SOFT | 60x60 cm Rect LUX | 60x60 cm Rect NATURALE | 60x60 cm Rect EXT | |
| | 60x120 cm Rect SOFT | 60x120 cm Rect LUX | 60x120 cm Rect NATURALE | 60x120 cm Rect EXT | 60x120 cm Rect STRUTTURATO |
| | 120x120 cm Rect SOFT | 120x120 cm Rect LUX | | | |
| Surfaces | NATURALE EXT STRUTTURATO SOFT - Recommended for flooring in residential and low traffic commercial spaces. LUX - Recommended, as well as for wall cladding, also for flooring in residential or light commercial areas that are not subjected to heavy traffic, where anti-slip characteristics are not required. The occasional presence of small inconsistencies or little spots on the surface is to be considered a characteristic of the material and of its unique production process. If the product is laid in direct contact with external environments, it is recommended to use protective solutions to reduce the formation of scratches. | | | | |
| Edges | RECTIFIED (RECT) | | | | |
| Thickness | 9 mm – 20mm | | | | |



Tender specifications | PERPETUAL collection

Technical features

Product type: coloured-body porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

| Technical features | | Test method | Required values ISO 13006-G / EN 14411-G Bla-UGL Group | Average values PERPETUAL |
|--------------------------------|-----------------------|--------------|--|---|
| Water absorption | | ISO 10545-3 | ≤ 0,5% | 0,05% |
| Breaking strength (S) | | ISO 10545-4 | ≥ 1300 N | Thickness 9 mm: 2200 N Thickness 20 mm: 13600N |
| Modulus of rupture | | ISO 10545-4 | ≥ 35 N/mm ² | 50 N/mm ² |
| Deep abrasion resistance | | ISO 10545-6 | ≤ 175 mm ³ | 145 mm ³ (NATURALE, EXT, STRUTTURATO, SOFT) COMPLIANT (LUX) |
| Linear thermal expansion | | ISO 10545-8 | No provision | α ≤ 7 · 10 ⁻⁶ °C ⁻¹ |
| Stain resistance | | ISO 10545-14 | Class 3 min. | 5 RESISTANT |
| Chemical resistance (*) | | ISO 10545-13 | As indicated by manufacturer | LA, HA RESISTANT |
| Frost resistance | | ISO 10545-12 | No alteration | RESISTANT |
| Dimensions | Lenght and width | ISO 10545-2 | RECT ± 0,3%, max ± 1 mm | COMPLIANT |
| | Straightness of sides | ISO 10545-2 | RECT ± 0,3%, max ± 0,8 mm | COMPLIANT |
| | Rectangularity | ISO 10545-2 | RECT ± 0,3%, max ± 1,5 mm | COMPLIANT |
| | Warpage | ISO 10545-2 | RECT ± 0,4%, max ± 1,8 mm | COMPLIANT |
| | Thickness | ISO 10545-2 | RECT ± 5%, max ± 0,5 mm | COMPLIANT |
| Slip resistance | DIN EN 16165- Annex B | - | - | R10 (NATURALE) |
| | DIN EN 16165- Annex A | - | - | R11 (STRUTTURATO, EXT) |
| | DIN EN 16165- Annex C | - | - | C (STRUTTURATO, EXT) |
| | BCR TORTUS | - | - | μ > 0,40 (NATURALE, EXT , STRUTTURATO) |
| | ANSI A326.3 | - | - | ID - DCOF ≥ 0,42 (Dry): NATURALE, SOFT, LUX IW - DCOF ≥ 0,42 (Dry): NATURALE, SOFT EW: EXT, STRUTTURATO |
| | AS/NZS 4586 | - | - | P4: EXT, STRUTTURATO |
| Shade variation | | ANSI A137.1 | As indicated by manufacturer | V2 (Onice Clear) V3 (Venato Gold - Orobico Blend - Belvedere Dark, Travertino Ivory, Travertino Cream) V4 (Breccia Warm) |
| Fire reaction | | EN 13823 | CPR (UE) 305/2011, 2000/147/CE, UNI EN 13501-1 | Class A1 (wall) |
| | | EN 9239-1 | | Class A1 _{fl} (floor) |
| Thermal conductivity | | EN 12524 | - | λ = 1,3 W/m °K |
| Recommended minimum joint (**) | | Indoor | - | 2 mm (RECT) |
| | | Outdoor | - | 5/6mm (RECT) |

(*) Excluding hydrofluoric acid and its derivatives.

(**) The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.